

# STABURAGS NBU 30 PTM

Lubricating and assembly grease



## Your benefits at a glance

- Assembly grease protecting against tribo-corrosion
- Good corrosion protection
- Excellent resistance to water even under outdoor conditions
- Approved by the company Knorr Bremse, N 12006-37

## Your requirements - our solution

STABURAGS NBU 30 PTM is an assembly grease containing a solid lubricant. It is resistant to water and protects against tribo-corrosion (fretting corrosion). It has proven effective in outdoor applications subject to high humidity.

### Application

STABURAGS NBU 30 PTM is suitable as an assembly grease for applications incorporating sliding clearance fits. Applications include hot and cold water valves and taps, slideways (especially in filling machines), valve spindles and cylinder guides. The product can also be used as a sealing grease. In addition, it is suitable for the lubrication of slideways, bolts, spindles and screws, e.g. in railway bogie assemblies.

STABURAGS NBU 30 PTM is especially suitable for external brake components of rail vehicles, such as bolts and rods.

STABURAGS NBU 30 PTM facilitates assembly and disassembly of ABS sensors in vehicles.

## Application notes

Use the aerosol spray version of STABURAGS NBU 30 PTM for relubrication of railway brake parts where no grease nipple is incorporated. For optimum penetration into fine clearances we recommend spraying for at least 8 seconds. This will increase efficiency of brake rods in rail vehicles thus ensuring the longest maintenance intervals.

When used for assembly and lubricating purposes we recommend the lubricant be lightly applied to the component surfaces via a lint free cloth, by hand, or by brush.

STABURAGS NBU 30 PTM shows good adhesive strength at low temperatures down to min. -55 °C.

## Material safety data sheets

Material safety data sheets can be requested via our website [www.klueber.com](http://www.klueber.com). You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	STABURAGS NBU 30 PTM	STABURAGS NBU 30 PTM Spray
Cartridge 450 g	+	
Aerosol can 250 ml		+
Can 1,2 kg	+	
Bucket 30 kg	+	
Drum 220 kg	+	

## Hint

Except for the article number and the minimum shelf life, the spray data below refer to the solvent-free spray agent.

# STABURAGS NBU 30 PTM

Lubricating and assembly grease



Characteristics	STABURAGS NBU 30 PTM	STABURAGS NBU 30 PTM Spray
Article number	017069	081275
Composition	solid lubricant	solid lubricant
Composition, thickener	barium complex soap	barium complex soap
Composition, type of oil	mineral oil	mineral oil
Colour space	grey	grey
Service temperature, lower limit	-10 °C	-10 °C
Service temperature, upper limit	160 °C	160 °C
Density, Klüber method: PN 024, 20°C	approx. 1.10 g/cm <sup>3</sup>	approx. 1.10 g/cm <sup>3</sup>
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	245 0.1 mm	245 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	275 0.1 mm	275 0.1 mm
Shear viscosity, Klüber method: PN 008@DIN 53019-1, equipment: rotational viscometer, 25°C, 300 s <sup>-1</sup>	approx. 15000 mPas	approx. 15000 mPas
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 51562-1 / ASTM D445 / ASTM D7042, 100°C	approx. 31 mm <sup>2</sup> /s	approx. 31 mm <sup>2</sup> /s
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 51562-1 / ASTM D445 / ASTM D7042, 40°C	approx. 490 mm <sup>2</sup> /s	approx. 490 mm <sup>2</sup> /s
Dropping point, DIN ISO 2176 / IP 396	≥ 220 °C	≥ 220 °C
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	60 months	24 months

## Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 90 years.

Klüber Lubrication München GmbH & Co. KG /  
Geisenhausenerstraße 7 / 81379 München / Germany /  
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.