

Klüberplex BE 11-462

Mineral oil based rolling and sliding bearing grease



Your benefits at a glance

- Free from heavy metals and chlorine
- Wide service temperature range
- Suitable for lubrication points exposed to high loads
- Adhesive
- Resistant to water

Your requirements - our solution

Klüberplex BE 11-462 is a mineral oil based, aluminium complex saponified grease for rolling and sliding bearings. It is free from heavy metals and chlorine, protects well against wear and is highly pressure absorptive. Other features of Klüberplex BE 11-462 include excellent adhesiveness, water resistance and protection against corrosion.

Application

Klüberplex BE 11-462 is designed for the lubrication of rolling and sliding bearings as well as slide- and guide-ways within a wide range of temperatures. It is ideal for use as a multi-purpose grease in the base materials industry, for lubrication points exposed to high loads in the iron and steel industries, and for long-term lubrication of construction machines and earthmovers.

Application notes

Klüberplex BE 11-462 can be applied by grease gun, brush, spatula, or automatic lubrication.

Service temperature range

The recommended temperature range for Klüberplex BE 11-462 is between -15 °C and 150 °C. For consumptive lubrication, the range may be extended up to approx. 200 °C depending on relubrication. Service temperatures are approximations and may vary with lubricant composition, intended use, and method of application.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klüberplex BE 11-462	Klüberplex BE 11-462 Spray
Aerosol can 400 ml		+
Can 1 kg	+	
Bucket 25 kg	+	
Drum 180 kg	+	

Hint

Except for the article number and the minimum shelf life, the spray data below refer to the solvent-free spray agent.

Characteristics	Klüberplex BE 11-462	Klüberplex BE 11-462 Spray
Article number	097111	081007

Klüberplex BE 11-462

Mineral oil based rolling and sliding bearing grease



Characteristics	Klüberplex BE 11-462	Klüberplex BE 11-462 Spray
Appearance	transparent	transparent
Colour space	brown	brown
Texture	homogeneous , short fibrous	homogeneous , short fibrous
Service temperature, lower limit		-15 °C
Service temperature, upper limit		150 °C
Density, Klüber method: PN 024, 20°C	approx. 0.92 g/cm ³	approx. 0.92 g/cm ³
NLGI grade, DIN 51818	2	2
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	265 0.1 mm	265 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	295 0.1 mm	295 0.1 mm
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 51562-1 / ASTM D445 / ASTM D7042, 100°C	approx. 32 mm ² /s	approx. 30 mm ² /s
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 51562-1 / ASTM D445 / ASTM D7042, 40°C	approx. 500 mm ² /s	approx. 500 mm ² /s
SKF-EMCOR, DIN 51802, Klüber method: distilled water, 168 h	≤ 1 corrosion degree	≤ 1 corrosion degree
Dropping point, DIN ISO 2176 / IP 396	≥ 230 °C	≥ 230 °C
FAG FE9 rolling bearing test, DIN 51821-2, based on standard, 1500 / 3000-150, service life F50	≥ 100 h	≥ 100 h
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months	36 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 90 years.

Klüber Lubrication München GmbH & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.