

Klüberplus SK 02-295

Lubricating wax



Your benefits at a glance

- Non-polluting
- Wax-like texture
- Protects against wear and reduces friction in the boundary and mixed friction regimes
- No stick-slip
- Very low friction coefficient
- Water hazard category 1
- NSF H1-registered

Your requirements - our solution

Klüberplus SK 02-295 is a lubricating wax based on a combination of high-molecular synthetic hydrocarbons.

It offers good protection against friction, wear, tribo-corrosion and rust. It prevents stick slip and ensures good lubricity particularly in the boundary and mixed friction regimes, i.e. in cases of minor sliding movements or speeds and specifically high loads. The lubricating effect is also excellent between friction components made of different materials, especially aluminium alloys.

Tests carried out with the Tannert sliding indicator have confirmed the good lubricating properties of Klüberplus SK 02-295. Almost all friction coefficients were clearly below 0.1 and no stick slip movement occurred.

An essential property is that the consistent wax becomes liquid with increasing temperatures – between 45 °C and 75°C – and still offers good adhesion properties. In tests with a horizontal plate (steel ST 14) Klüberplus SK 02-295 did not run off when the plate was heated to 100 °C. Prior to testing, when the plate was still cold, approx. 6 g/m² of Klüberplus SK 02-295 were applied.

The texture is reversible. When cooling down, Klüberplus SK 02-295 becomes consistent again as soon as the temperature is below the softening range (45–75 °C). In its consistent texture the lubricating wax is extremely resistant to low temperatures and stable.

Klüberplus SK 02-295 is very resistant to oxidation.

It can be applied where incidental, technically unavoidable contact with food products may occur. Klüberplus SK 02-295 is generally recognized as safe, non-toxic and non-hazardous to the environment. It is classified in water hazard category 1 (not hazardous).

In addition, Klüberplus SK 02-295 offers very good protection against corrosion. During tests in a condensation water-alternating

climate (DIN 50 017 KFW) a corrosion rating of 0 was achieved after 30 cycles (720 h). This is equivalent to the performance of high-quality corrosion inhibitors. Consequently, Klüberplus SK 02-295 is substantially more efficient than e.g. hydraulic oils.

Klüberplus SK 02-295 is NSF H1 registered and therefore complies with FDA 21 CFR § 178.3570. The lubricant was developed for incidental contact with products and packaging materials in the food-processing, cosmetics, pharmaceutical or animal feed industries. The use of Klüberplus SK 02-295 can contribute to increase reliability of your production processes. We nevertheless recommend conducting an additional risk analysis, e.g. HACCP.

Application

Klüberplus SK 02-295 was developed for industrial applications, e.g.

- all types of press fits for easier fitting of pins, bolts and bushings
- sliding guides for stick-free smooth sliding
- sliding points for long-term and lifetime lubrication in case of mixed friction
- hinges for non-tacky, clean lubrication to prevent squeaking
- screws for low friction, steady tightening
- ropes for smooth handling and reliable protection against corrosion
- shaft/hub connection for protection against tribo-corrosion and fretting corrosion

Klüberplus SK 02-295 is very useful for metal-forming processes, e.g. deep-drawing of CrNi steel, aluminium sheet and threading or drilling of plates. The efficiency was verified in many mechano-dynamical tests and has been proven in practice.

Klüberplus SK 02-295

Lubricating wax



Application notes

Cold application

Klüberplus SK 02-295 is applied manually on polished surfaces three or four times and on normal surfaces twice without any auxiliary means, thus obtaining a layer of approx. 6 µm. Film thickness also depends on the force and speed applied during application.

Hot application

If possible, Klüberplus SK 02-295 should be applied to preheated surfaces. This allows a faster and more homogeneous application of

the lubricating wax and results in lower friction coefficients. Heating the component surfaces to 50–70 °C has proven most efficient.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Supplementary data	Klüberplus SK 02-295		Mineral hydrocarbon oil CL (ISO-VG 46)		Lithium soap based grease	
load	50 N corresponds to 0.46 N/mm ²	300 N corresponds to 2.75 N/mm ²	50 N corresponds to 0.46 N/mm ²	300 N corresponds to 2.75 N/mm ²	50 N corresponds to 0.46 N/mm ²	300 N corresponds to 2.75 N/mm ²
steel / aluminium	0.065	0.050	0.244	stick-slip at 100 N	0.18	0.137
steel / copper	0.066	0.054	stick-slip	-	0.216	stick-slip at 100 N
steel / steel	0.084	0.072	stick-slip	-	stick-slip	-
aluminium / aluminium	0.184	0.122	0.22	0.185	0.19	stick-slip at 250 N

Friction coefficients determined with the Tannert sliding indicator; for Klüberplus SK 02-295 determined during hot application.

Pack sizes	Klüberplus SK 02-295
Can 1 kg	+
Bucket 20 kg	+

Characteristics	Klüberplus SK 02-295
Article number	012166
Composition, thickener	wax
Colour space	yellow
Service temperature, lower limit	-40 °C
Service temperature, upper limit	120 °C
NSF H1 registration number	136216
needle penetration, DIN ISO 51579, 25°C	approx. 25 0.1 mm
Corrosion test, DIN EN ISO 6270-2, AHT	≥ 1 (30) corrosion degree (cycles)
Dropping point, DIN ISO 2176 / IP 396	75-82 °C
Water resistance, DIN 51807-1, based on standard, 24 h, 50°C	0 - 50 rating

Klüberplus SK 02-295

Lubricating wax



Characteristics

Klüberplus SK 02-295

Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened 60 months original container, approx.

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 90 years.

Klüber Lubrication München GmbH & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.