

Klübersynth LP 42-32

Low-temperature grease with solid lubricant



Your benefits at a glance

- Synthetic low-temperature grease
- Inhibits fretting corrosion
- Thermally stable, does not become pasty
- High resistance to wear and corrosion
- UV indicator for quality assurance at 366 nm
- Starter grease acc. to Bosch standard N28 FT 1022-002 (formerly VS 18570-Ft)

Your requirements - our solution

Klübersynth LP 42-32 is a dynamically light, fully synthetic lubricating grease. The service temperature range is approx. -50 °C to 150 °C. In contrast to conventional greases, Klübersynth LP 42-32 does not become pasty under thermal load, and its flow limit is not increased. Instead, this grease becomes a little softer, thus preventing wear particles and dust from making the lubricant pasty. Lubricity is ensured for a longer period. The product's good ageing resistance and its excellent corrosion and wear protection make it an ideal long-term and lifetime lubricant. Machine elements lubricated with Klübersynth LP 42-32, achieve very low starting and running torques even at extremely low temperatures.

Application

Owing to its excellent low-temperature characteristics, Klübersynth LP 42-32 is the preferred product for metal/metal contacts in the automotive industry. It reduces abrasive wear and fretting corrosion, and extends the life of machine elements which operate in the mixed friction regime and are subject to shocks and vibrations. Klübersynth LP 42-32 is used in helical splines, pinion bearings and sleeves with lubricating pockets and planetary gears used in starters.

Application notes

Klübersynth LP 42-32 is applied by brush or spatula, or with conventional metering systems.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klübersynth LP 42-32
Can 1 kg	+
Bucket 25 kg	+
Bucket 50 kg	+
Characteristics	Klübersynth LP 42-32
Article number	004153
Colour space	beige
Texture	homogeneous , short fibrous
Service temperature, lower limit	-50 °C

Klübersynth LP 42-32

Low-temperature grease with solid lubricant



Characteristics	Klübersynth LP 42-32
Service temperature, upper limit	150 °C
Density, Klüber method: PN 024, 20°C	approx. 1.00 g/cm ³
NLGI grade, DIN 51818	2
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	265 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	295 0.1 mm
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 51562-1 / ASTM D445 / ASTM D7042, 100°C	approx. 5 mm ² /s
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 51562-1 / ASTM D445 / ASTM D7042, 40°C	approx. 25 mm ² /s
Copper corrosion, DIN 51811, 24 h, 120°C	≤ 2 - 120 - 24 corrosion degree
SKF-EMCOR, DIN 51802, Klüber method: distilled water, 168 h	≤ 1 corrosion degree
Oil separation, ASTM D6184, 30 h, 100°C	≤ 6 % by weight
Flow pressure, DIN 51805-2, -50°C	≤ 1400 mbar
Dropping point, DIN ISO 2176 / IP 396	≥ 180 °C
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx. 24 months	

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 90 years.

Klüber Lubrication München GmbH & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.